Amendments to the Claims:

The listing of claims will replace all prior versions, and listings, of claims in the application:

Listing of Claims:

- 1. (currently amended) A heat-cured furan binder system comprising:
 - (a) from 5 to 90 5 to 50 parts by weight of a furan resin;
 - (b) from 5 to 90 5 to 50 parts by weight of furfuryl alcohol; and
 - (c) from 1-to 90 5 to 50 parts by weight of a furan monomer or oligomer containing at least two terminal hydroxymethyl groups dimethyloated furan selected from the group consisting of dimethylolated furan monomers, dimethylolated furan oligomers, and mixtures thereof,
 - (d) from 1 to 10 parts by weight of polyvinyl acetate; and
 - (e) from 1 to 10 parts by weight of an activator selected from the group consisting of resorcinol pitch, bisphenol A tar, and mixtures thereof,

wherein said parts by weight are based upon 100 parts of binder resin.

- 2. (canceled)
- 3. (canceled)
- 4. (currently amended) The binder of claim 3 1, which further comprises a silane.

5. (canceled)			
6. (canceled)	6. (canceled)		
7. (currently a	amende	ed) The binder of claim 6 4, which does not contain a polyol.	
8. (currently a	tly amended) A foundry mix comprising in admixture:		
	(a)	a major amount of a foundry aggregate;	
	(b)	a catalytically effective amount of a salt of a strong inorganic or organic acid; and	
	(c)	a minor amount of a foundry binder of claims 1, 2, 3, 4, 5, 6, or 7.	
	catalyst is from 10 parts by weight to 40 parts by weight based upon 100 parts binder. 10. (original) A process for preparing a workable foundry shape comprising: A. forming a foundry mix of claim 9; B. shaping the foundry mix of A into a foundry shape;		
В.			
C.	contacting the foundry shape of B with a source of heat at a temperature sufficient to cure said mix; and		
D.	D. allowing the foundry shape to harden into a workable foundry shape.		
11. (original)	11. (original) A foundry shape prepared in accordance with claim 10.		
12. (canceled)	2. (canceled)		
13. (canceled)	3. (canceled)		

.

.